



Zytel® HTNFR52G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Zytel® HTN high performance polyamide resins feature high retention of properties upon exposure to elevated temperature, to high moisture, and to harsh chemical environments. Polymer families and grades of Zytel® HTN are tailored to optimise performance as well as processability.

Typical applications with Zytel® HTN include demanding applications in the automotive, electrical and electronics, domestic appliances, and construction industries.

Zytel® HTNFR52G30NH NC010 is a 30% glass reinforced, flame retardant high performance polyamide resin. It is also a PPA resin and it uses a non-halogenated flame retardant.

Product information

Resin Identification	PA6T/66-GF30FR(40)	ISO 1043
Part Marking Code	>PA6T/66-GF30FR(40)<	ISO 11469
Part Marking Code	>PPA-GF30FR<	SAE J1344
ISO designation	ISO 16396-PA6T/66,GF30 FR(40),M1F1GNR,S10-100	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.3/-	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.1/-	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile Modulus	10500/10500	MPa	ISO 527-1/-2
Stress at break	150/130	MPa	ISO 527-1/-2
Strain at break	2.2/2	%	ISO 527-1/-2
Flexural Modulus	9000/10000	MPa	ISO 178
Flexural Strength	230/200	MPa	ISO 178
Charpy impact strength, 23°C	45/40	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	40/35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	8/7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	7/7	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34/0.34	-	

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	312/*	°C	ISO 11357-1/-3
Melting temperature, first heat	310/*	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	283/*	°C	ISO 75-1/-2
Ball pressure test	290/-	°C	IEC 60695-10-2
CLTE, Parallel, -40-23°C	20/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	20/*	E-6/K	ISO 11359-1/-2
CLTE, Parallel, 55-160°C	20/*	E-6/K	ISO 11359-1/-2
CLTE, Normal, -40-23°C	60/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	60/*	E-6/K	ISO 11359-1/-2



Zytel® HTNFR52G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Coeff. of linear therm. expansion, Normal, 55-160°C	100/*	E-6/K	ISO 11359-1/-2
RTI, electrical, 0.4mm	140	°C	UL 746B
RTI, electrical, 0.75mm	140	°C	UL 746B
RTI, electrical, 1.5mm	140	°C	UL 746B
RTI, electrical, 3mm	140	°C	UL 746B
RTI, impact, 0.75mm	115	°C	UL 746B
RTI, impact, 1.5mm	115	°C	UL 746B
RTI, impact, 3mm	120	°C	UL 746B
RTI, strength, 0.75mm	125	°C	UL 746B
RTI, strength, 1.5mm	125/*	°C	UL 746B
RTI, strength, 3mm	130	°C	UL 746B

Flammability

		dry/cond.	
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Thickness tested	1.5/*	mm	IEC 60695-11-10
UL recognition	yes/*	-	UL 94
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.4/*	mm	IEC 60695-11-10
UL recognition	yes/*	-	UL 94
Oxygen index	37/*	%	ISO 4589-1/-2
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	725/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 0.4mm	700/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 3mm	800/-	°C	IEC 60695-2-13
FMVSS Class	DNI	-	ISO 3795 (FMVSS 302)

Electrical properties

		dry/cond.	
Relative permittivity, 100Hz	4.1/-	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.9/-	-	IEC 62631-2-1
Dissipation factor, 100Hz	65/-	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	120/-	E-4	IEC 62631-2-1
Volume resistivity	>1E13/5E11	Ohm.m	IEC 62631-3-1
Surface resistivity	*/>1E15	Ohm	IEC 62631-3-2
Electric strength	36/-	kV/mm	IEC 60243-1
Comparative tracking index	600/-	-	IEC 60112
Electric Strength, Short Time, 2mm	26/-	kV/mm	IEC 60243-1
Dielectric Constant, 1 GHz	3.7/-	-	ASTM D 2520 B
Dielectric Constant, 10 GHz	3.8/-	-	ASTM D 2520 B
Dissipation Factor, 1 GHz	110/-	E-4	ASTM D 2520 B
Dissipation Factor, 10 GHz	100/-	E-4	ASTM D 2520 B



Zytel® HTNFR52G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Other properties

Density	dry/cond.	1440/-	kg/m ³	ISO 1183
---------	-----------	--------	-------------------	----------

VDA Properties

Odour		3.5 class		VDA 270
-------	--	-----------	--	---------

Injection

Drying Recommended	yes
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	6 - 8 h
Processing Moisture Content	≤0.1 %
Min. melt temperature	320 °C
Max. melt temperature	325 °C
Min. mould temperature	90 °C
Max. mould temperature	130 °C

Characteristics

Additives	Release agent, Flame retardant, Non-halogenated/Red phosphorous free flame retardant
-----------	--

Additional Information


Injection molding	For molding machine components, use corrosion resistant and wear resistant steel. For details please contact your DuPont representative. Limit the residence time of the resin in the machine. Use proper protective equipment and adequate ventilation.
-------------------	--



Zytel® HTNFR52G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Stress-strain (dry)






Zytel® HTNFR52G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Stress-strain (cond.)






Zytel® HTNFR52G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Secant modulus-strain (dry)






Zytel® HTNFR52G30NH NC010

HIGH PERFORMANCE POLYAMIDE RESIN

Secant modulus-strain (cond.)



Revised: 2020-08-12

Page: 7 of 7

dupont.com

The information set forth herein is furnished free of charge, is based on technical data that DuPont believes to be reliable, and represents typical values that fall within the normal range of properties. This information relates only to the specific material designated and may not be valid for such material used in combination with other materials or in other processes. It is intended for use by persons having technical skill, at their own discretion and risk. This information should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards and comply with applicable law. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract or other acknowledgement that is consistent with the DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative.

DuPont's sole warranty is that our products will meet our standard sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DUPONT SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE, MERCHANTABILITY, OR NON-INFRINGEMENT. DUPONT DISCLAIMS LIABILITY FOR ANY SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2021 DuPont. All rights reserved.