

# Product Information **Ultraform®**

## N2520 L

03/2014

### POM



#### Product description

This grade has reduced electrical surface resistivity.

Abbreviated designation according to ISO 1043: POM  
Designation according to ISO 9988-1: POM-K, M-GRY, 03-002

#### Physical form and storage

Ultraform® is supplied in the form of granules having a bulk density of approx. 850 g/l. Standard pack is the 1000 kg Oktabin (octagonal container). Ultraform® is not subject to change when it is stored in dry, ventilated rooms. After relatively long storage (>1 year) or when handling material from previously opened containers, preliminary drying is recommended in order to remove any moisture which has been absorbed.

#### Product safety

Ultraform® is not a hazardous material as defined in the German Ordinance on Hazardous Materials.

If Ultraform® is processed properly little or no formaldehyde occurs in the region of the processing machine. Measures should be taken to ensure ventilation and venting of the work area, preferably by means of an extraction hood over the barrel unit.

Ultraform® decomposes when subjected to excessive heat. The decomposition products formed in this case consist almost exclusively of formaldehyde, a gas which has a pungent smell even at very low concentrations and irritates the mucous membranes. Decomposition can rapidly result in the build-up of a high gas pressure in the barrel of the processing unit. If the die is sealed there may be a sudden release of pressure via the filling hopper.

Contamination of Ultraform® by thermoplastics that cause decomposition of polyacetals, e.g. PVC or plastics containing halogenated fire protection agents, must be avoided under all circumstances. Even small quantities can cause uncontrolled and rapid decomposition of Ultraform® during processing.

Pellets and finished parts must not be allowed to be exposed to environmental conditions which cause decomposition of Ultraform® e.g. contact with strong acids or intensive irradiation e.g. in outdoor applications.

Detailed safety and environmental information is contained in the Ultraform® brochure and the material safety data sheet. Both are available from the PlasticsPortal, [www.plasticsportal.net](http://www.plasticsportal.net), or the Ultra-Infopoint under phone +49-621-60-78780 or fax +49-621-60-78730.

#### Note

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. In order to check the availability of products please contact us or our sales agency.

## Product Information

| Typical values for uncoloured product at 23 °C <sup>1)</sup>                         | Test method       | Unit                   | Values <sup>2)</sup> |
|--|-------------------|------------------------|----------------------|
| <b>Properties</b>  |                   |                        |                      |
| Polymer abbreviation   | -                 | -                      | <b>POM</b>           |
| Density  | ISO 1183          | kg/m <sup>3</sup>      | <b>1400</b>          |
| Water absorption, equilibrium in water at 23°C                                       | similar to ISO 62 | %                      | <b>0.8</b>           |
| Moisture absorption, equilibrium 23°C/50% r.h.                                       | similar to ISO 62 | %                      | <b>0.20</b>          |
| <b>Processing</b>  |                   |                        |                      |
| Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)                 | -                 | -                      | <b>M</b>             |
| Melting temperature, DSC   | ISO 11357-1/-3    | °C                     | <b>166</b>           |
| Melt volume-flow rate MVR at 190 °C and 2.16 kg                                      | ISO 1133          | cm <sup>3</sup> /10min | <b>7</b>             |
| Melt temperature, injection moulding   | -                 | °C                     | <b>190 - 220</b>     |
| Mould temperature, injection moulding  | -                 | °C                     | <b>60 - 120</b>      |
| Molding shrinkage (parallel)   | ISO 2577, 294-4   | %                      | <b>2.10</b>          |
| Molding shrinkage (normal)   | ISO 2577, 294-4   | %                      | <b>2.10</b>          |
| <b>Flammability</b>  |                   |                        |                      |
| UL94 rating at 1,6 mm thickness  | IEC 60695-11-10   | class                  | <b>HB</b>            |
| Automotive materials (thickness d >= 1mm) <sup>3)</sup>                              | FMVSS 302         | -                      | <b>+</b>             |
| <b>Mechanical properties</b>   |                   |                        |                      |
| Tensile modulus  | ISO 527-1/-2      | MPa                    | <b>2400</b>          |
| Yield stress, 50 mm/min <sup>4)</sup>  | ISO 527-1/-2      | MPa                    | <b>50</b>            |
| Yield strain, 50 mm/min <sup>4)</sup>  | ISO 527-1/-2      | %                      | <b>6</b>             |
| Nominal strain at break, 50 mm/min   | ISO 527-1/-2      | %                      | <b>7</b>             |
| Charpy unnotched impact strength (23°C)  | ISO 179/1eU       | kJ/m <sup>2</sup>      | <b>40</b>            |
| Charpy notched impact strength (23°C)  | ISO 179/1eA       | kJ/m <sup>2</sup>      | <b>4</b>             |
| Ball indentation hardness at 358 N and 30 s  | ISO 2039-1        | MPa                    | <b>120</b>           |
| <b>Thermal properties</b>  |                   |                        |                      |
| HDT A (1.80 MPa)   | ISO 75-1/-2       | °C                     | <b>85</b>            |
| Max. service temperature (short cycle operation)                                     | -                 | °C                     | <b>100</b>           |
| Coefficient of linear thermal expansion, longitudinal (23-55)°C                      | ISO 11359-1/-2    | E-6/K                  | <b>120</b>           |
| <b>Electrical properties</b>   |                   |                        |                      |
| Relative permittivity (1 MHz)  | IEC 60250         | -                      | <b>120</b>           |
| Dissipation factor (1 MHz)   | IEC 60250         | E-4                    | <b>5300</b>          |
| Surface resistivity  | IEC 60093         | Ohm                    | <b>1E07</b>          |
| Volume resistivity, ASTM D-4496 according to SAE J1645/ISO 3915, 4 point measurement | ISO 3915          | Ohm*cm                 | <b>500</b>           |
| Electric strength K20/P50  | IEC 60243-1       | kV/mm                  | <b>85</b>            |

## Footnotes

- 1) If product name or properties don't state otherwise.
- 2) The asterisk symbol "\*" signifies inapplicable properties.
- 3) + = passed
- 4) typically 80 to 90 % of the tensile bars show a yielding point

BASF SE

67056 Ludwigshafen, Germany