

### Product Description

Ultramid A3Z HP UN is an unreinforced, impact modified, heat stabilized, high flow PA66 injection molding grade. Ultramid A3Z HP UN offers a unique combination of maximum toughness and impact resistance with excellent high flow processability.

PHYSICAL	ISO Test Method	Property Value	
Density, g/cm <sup>3</sup>	1183	1.07	
MECHANICAL	ISO Test Method	Dry	Conditioned
Tensile Modulus, MPa	527		
23°C		1,900	1,060
Tensile stress at yield, MPa	527		
23°C		50	-
Tensile strain at yield, %	527		
23°C		5	-
Nominal strain at break, %	527		
23°C		45	>50
Flexural Modulus, MPa	178		
23°C		1,800	880
IMPACT	ISO Test Method	Dry	Conditioned
Izod Notched Impact, kJ/m <sup>2</sup>	180		
-40°C		23	18
23°C		80	99
Charpy Notched, kJ/m <sup>2</sup>	179		
-30°C		28	19
23°C		90	113
Charpy Unnotched, kJ/m <sup>2</sup>	179		
-30°C		N	N
23°C		N	N
THERMAL	ISO Test Method	Dry	Conditioned
Melting Point, °C	3146	260	-
HDT A, °C	75	64	-
HDT B, °C	75	170	-
UL RATINGS	UL Test Method	Property Value	
Flammability Rating, 0.75mm	UL94	HB	
Relative Temperature Index, 0.75mm	UL746B		
Mechanical w/o Impact, °C		110	
Mechanical w/ Impact, °C		105	
Electrical, °C		140	
Flammability Rating, 3.0mm	UL94	HB	
Relative Temperature Index, 3.0mm	UL746B		
Mechanical w/o Impact, °C		110	
Mechanical w/ Impact, °C		105	
Electrical, °C		140	

### Processing Guidelines

#### Material Handling

Nylon 66 materials must be properly dried in order to provide parts with optimum strength and toughness. Nylon 66 materials are hygroscopic and will become degraded by excessive moisture during the injection molding process. For unopened bag/box, dry at 60 degC (140 degF) for 1-2 hours. For material exposed to the atmosphere, if additional drying is needed, dry at 66 degC (150 degF) or until the moisture level is between 0.04 - 0.20%.

#### Typical Profile

Melt Temperature: 288-305 degC (550-581 degF)  
Mold Temperature: 60-100 degC (140-212 degF)  
Injection Pressure: 35-125 MPa (5000-18000 psi)

Back Pressure: 0-0.35 MPa (0-50 psi)  
Screw RPM 40-80  
Screw Compression Ratio:3:1-4:1

#### Mold Temperatures

This product can be processed over a wide range of mold temperatures; however, for applications where aesthetics are critical, a mold surface temperature of 60-100 degC (140-212 degF) is recommended.

#### Pressures

Injection pressure controls the filling of the part and should be applied for 90% of ram travel. Packing pressure affects the final part and can be used effectively in controlling sink marks and shrinkage. It should be applied and maintained until the gate area is completely frozen off.

**Fill Rate**

Fast fill rates are recommended to ensure uniform melt delivery to the cavity and prevent premature freezing.

**Note**

Although all statements and information in this publication are believed to be accurate and reliable, they are presented gratis and for guidance only, and risks and liability for results obtained by use of the products or application of the suggestions described are assumed by the user. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH. Statements or suggestions concerning possible use of the products are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that toxicity data and safety measures are indicated or that other measures may not be required.

BASF Corporation  
Engineering Plastics  
1609 Biddle Avenue  
Wyandotte, MI 48192

General Information: 800-BC-RESIN  
Technical Assistance: 800-527-TECH (734-324-5150)  
Web address: <http://www.plasticsportal.com/usa>

