



# Solumer™ 871L

## **Polyolefin Elastomer**

#### Introduction

Solumer™ 871L is an ethylene-octene copolymer produced via Nexlene™ technology. Solumer™ 871L performs well in a wide range of general purpose thermoplastic elastomer applications and has excellent flow characteristics.

#### **Applications**

- General purpose thermoplastic elastomers
- Wire and cable

- Impact modification
- Footwear

### **Properties**

			Typical Values	Unit	Test Method
Physical	Density		0.868	g/cm <sup>3</sup>	ASTM D792
Properties	Melt index (2.16 kg @190°C)		1.0	g/10min	ASTM D1238
	Mooney viscosity (ML1+4 @ 121°C)		21	MU	ASTM D1646
Mechanical	Tensile strength at break		95	kgf/cm <sup>2</sup>	ASTM D638 <sup>2</sup>
Properties <sup>1</sup>	Elongation at break		850	%	ASTM D638 <sup>2</sup>
	Tensile modulus (100% Elongation)		30	kgf/cm <sup>2</sup>	ASTM D638 <sup>2</sup>
	Flexural modulus (1% secant)		140	kgf/cm <sup>2</sup>	ASTM D790
	Tear strength (Type C)		41	kgf/cm <sup>2</sup>	ASTM D624
	Hardness	Shore A (1 sec)	72		ASTM D2240
		Shore D (1 sec)	21		ASTM D2240
Thermal	hermal Melting temperature		62	°C	SK Method
<b>Properties</b>	Glass transition temperature		-52	°C	SK Method

<sup>&</sup>lt;sup>1</sup> Evaluated using compression molded sample

These are typical values and are not be construed as specifications. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK Global Chemical Co.,LTD 26 Jong-ro, Jongno-gu, Seoul, Korea TEL +82-2-2121-6757

TS&D

SK innovation Global Technology 325 Exporo, Yueseong-gu, Daejeon, Korea TEL +82-42-609-8623

<sup>&</sup>lt;sup>2</sup> Crosshead speed: 500 mm/min