

LEXANT™ RESIN 103R

REGION ASIA

DESCRIPTION

LEXANT™ 103R resin is a 7 MFR polycarbonate, MVR of 6. UV Stabilized. Mold release. UL94 HB rated. UL746C f1 rated. Suitable for extrusion and injection molding applications.

TYPICAL PROPERTY VALUES

Revision 20201125

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	62	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	65	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	7	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	110	%	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	93	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2340	MPa	ASTM D790
Hardness, Rockwell M	70	-	ASTM D785
Hardness, Rockwell R	118	-	ASTM D785
Taber Abrasion, CS-17, 1 kg	10	mg/1000cy	ASTM D1044
IMPACT			
Izod Impact, unnotched, 23°C	3204	J/m	ASTM D4812
Izod Impact, notched, 23°C	907	J/m	ASTM D256
Tensile Impact Strength, Type S	546	kJ/m ²	ASTM D1822
Falling Dart Impact (D 3029), 23°C	169	J	ASTM D3029
THERMAL			
Vicat Softening Temp, Rate B/50	154	°C	ASTM D1525
HDT, 0.45 MPa, 6.4 mm, unannealed	137	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	132	°C	ASTM D648
CTE, -40°C to 95°C, flow	6.84E-05	1/°C	ASTM E831
Specific Heat	1.25	J/g·°C	ASTM C351
Thermal Conductivity	0.19	W/m·°C	ASTM C177
Relative Temp Index, Elec	130	°C	UL 746B
Relative Temp Index, Mech w/impact	130	°C	UL 746B
Relative Temp Index, Mech w/o impact	130	°C	UL 746B
PHYSICAL			
Specific Gravity	1.2	-	ASTM D792
Specific Volume	0.83	cm ³ /g	ASTM D792
Density	1.19	g/cm ³	ASTM D792
Water Absorption, (23°C/24hrs)	0.15	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.35	%	ASTM D570
Water Absorption, equilibrium, 100°C	0.58	%	ASTM D570
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	7	g/10 min	ASTM D1238
OPTICAL			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Light Transmission, 2.54 mm	88	%	ASTM D1003
Haze, 2.54 mm	1	%	ASTM D1003
Refractive Index	1.586	-	ASTM D542
ELECTRICAL			
Volume Resistivity	>1.E+17	Ω.cm	ASTM D257
Dielectric Strength, in air, 3.2 mm	14.9	kV/mm	ASTM D149
Relative Permittivity, 50/60 Hz	3.17	-	ASTM D150
Relative Permittivity, 1 MHz	2.96	-	ASTM D150
Dissipation Factor, 50/60 Hz	0.0009	-	ASTM D150
Dissipation Factor, 1 MHz	0.01	-	ASTM D150
Hot Wire Ignition {PLC}	4	PLC Code	UL 746A
High Voltage Arc Track Rate {PLC}	2	PLC Code	UL 746A
High Ampere Arc Ign, surface {PLC}	1	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	2	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	E45587-103028650	-	-
UL Yellow Card Link 2	E45587-236864	-	-
UL Recognized, 94HB Flame Class Rating	0.76	mm	UL 94
UV-light, water exposure /immersion	F1	-	UL 746C
INJECTION MOLDING			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	310 – 330	°C	
Nozzle Temperature	305 – 325	°C	
Front - Zone 3 Temperature	310 – 330	°C	
Middle - Zone 2 Temperature	300 – 320	°C	
Rear - Zone 1 Temperature	290 – 310	°C	
Mold Temperature	80 – 115	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.