

CYCOLOY™ FR RESINS CE3510

REGION EUROPE

DESCRIPTION

CYCOLOY CE3510 Polycarbonate/Acrylonitrile Butadiene Styrene (PC/ABS) blend is a high impact, non chlorinated/brominated flame retardant grade that can be injection molded or extruded. It has an MVR (260°C/5kg) of 8 and a UL94 V0@1.5mm flame rating.

TYPICAL PROPERTY VALUES

Revision 20190411

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, yld, Type I, 50 mm/min	64	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	49	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	4.3	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	35	%	ASTM D638
Tensile Modulus, 50 mm/min	2680	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	95	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2610	MPa	ASTM D790
Tensile Stress, yield, 50 mm/min	65	MPa	ISO 527
Tensile Stress, break, 50 mm/min	50	MPa	ISO 527
Tensile Strain, yield, 50 mm/min	4.6	%	ISO 527
Tensile Strain, break, 50 mm/min	>50	%	ISO 527
Flexural Stress, yield, 2 mm/min	95	MPa	ISO 178
Flexural Modulus, 2 mm/min	2470	MPa	ISO 178
IMPACT			
Izod Impact, notched, 23°C	664	J/m	ASTM D256
Izod Impact, notched, -30°C	109	J/m	ASTM D256
Izod Impact, unnotched 80*10*4 +23°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, unnotched 80*10*4 -30°C	NB	kJ/m ²	ISO 180/1U
Izod Impact, notched 80*10*4 +23°C	20	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 0°C	14	kJ/m ²	ISO 180/1A
Izod Impact, notched 80*10*4 -30°C	12	kJ/m ²	ISO 180/1A
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	45	kJ/m ²	ISO 179/1eA
Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm	14	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
Charpy -30°C, Unnotch Edgew 80*10*4 sp=62mm	NB	kJ/m ²	ISO 179/1eU
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	111	°C	ASTM D648
HDT, 1.82 MPa, 3.2mm, unannealed	100	°C	ASTM D648
Ball Pressure Test, 75°C +/- 2°C	PASSES	-	IEC 60695-10-2
Vicat Softening Temp, Rate B/50	116	°C	ISO 306
Vicat Softening Temp, Rate B/120	118	°C	ISO 306
HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm	111	°C	ISO 75/Be
HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm	100	°C	ISO 75/Ae
Relative Temp Index, Elec	90	°C	UL 746B

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Relative Temp Index, Mech w/impact	90	°C	UL 746B
Relative Temp Index, Mech w/o impact	90	°C	UL 746B
PHYSICAL			
Mold Shrinkage on Tensile Bar, flow	0.4 – 0.6	%	SABIC method
Mold Shrinkage on Tensile Bar, xflow	0.4 – 0.6	%	SABIC method
Specific Gravity	1.2	-	ASTM D792
Density	1.21	g/cm ³	ISO 1183
Melt Volume Rate, MVR at 260°C/5.0 kg	8	cm ³ /10 min	ISO 1133
ELECTRICAL			
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
Dielectric Strength, in oil, 0.8 mm	44	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 1.6 mm	27	kV/mm	IEC 60243-1
Dielectric Strength, in oil, 3.2 mm	18	kV/mm	IEC 60243-1
Comparative Tracking Index	225	V	IEC 60112
FLAME CHARACTERISTICS			
UL Recognized, 94V-2 Flame Class Rating	0.75	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating	1.5	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 1.0 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	825	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 3.0 mm	825	°C	IEC 60695-2-13
INJECTION MOLDING			
Drying Temperature	80 – 90	°C	
Drying Time	3 – 4	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	250 – 280	°C	
Nozzle Temperature	250 – 280	°C	
Front - Zone 3 Temperature	250 – 280	°C	
Middle - Zone 2 Temperature	245 – 275	°C	
Rear - Zone 1 Temperature	240 – 270	°C	
Hopper Temperature	60 – 80	°C	
Mold Temperature	60 – 80	°C	
PROFILE EXTRUSION			
Drying Temperature	80 – 85	°C	
Drying Time	2 – 4	Hrs	
Melt Temperature	230 – 270	°C	
Barrel - Zone 1 Temperature	235 – 260	°C	
Barrel - Zone 2 Temperature	240 – 265	°C	
Barrel - Zone 3 Temperature	245 – 270	°C	
Barrel - Zone 4 Temperature	245 – 270	°C	
Hopper Temperature	60 – 80	°C	
Adapter Temperature	245 – 270	°C	
Die Temperature	235 – 260	°C	
Calibrator Temperature	60 – 80	°C	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.